





SWC6 MAX Membrane Element

Performance:

Permeate Flow: Salt Rejection:

Boron Rejection (Typical)[†]:

Applied Pressure:

600 psi (4.1 MPa)

Low Pressure:

83.0%

< 0.1 PPM

113 °F (45 °C)

75 GPM (17.0 m³/h)

2-11 (1-13)*

1.0 NTU

6,600 gpd (25 m³/d)

99.6% (99.4 % min)

High Flow:

13,200 gpd (50 m3/d) 99.8% (99.7% min)

91.0%

800 psi (5.4 MPa)

Type Configuration: Spiral Wound

Membrane Polymer: Composite Polyamide 440 ft² (40.8m²) Membrane Active Area:

Application Data* Maximum Applied Pressure: 1200 psig (8.27 MPa)

> Maximum Chlorine Concentration: Maximum Operating Temperature: pH Range, Continuous (Cleaning): Maximum Feedwater Turbidity: Maximum Feedwater SDI (15 mins):

Maximum Feed Flow:

Minimum Ratio of Concentrate to


Permeate Flow for any Element:

5:1 Maximum Pressure Drop for Each Element: 10 psi

Test Conditions

The stated performance is initial (data taken after 30 minutes of operation), based on the following low pressure conditions:

> 32,000 ppm NaCl 600 psi (4.1 Mpa) Applied Pressure 77 °F (25 °C) Operating Temperature 10% Permeate Recovery 6.5 - 7.0 pH Range



A, inches (mm)	B, inches (mm)	C, inches (mm)	Weight, lbs. (kg)
40.0 (1016)	7.89 (200)	1.125 (28.6)	36 (16.4)

Permeate flow for individual elements may vary +25% or -15%. Membrane active area may vary +/-4%. Element weight may vary. All membrane elements are supplied with a brine seal, interconnector, and o-rings. Elements are enclosed in a sealed polyethylene bag containing less than 1.0% sodium meta-bisulfite solution, and then packaged in a cardboard box.

^{*} The limitations shown here are for general use. For specific projects, operating at more conservative values may ensure the best performance and longest life of the membrane. See Hydranautics Technical Bulletins for more detail on operation limits, cleaning pH, and cleaning temperatures.

When tested at standard test conditions with 5.0 ppm Boron in feed solution.